

		TEST METHOD	MIN	MAX
1	Saybolt Furol viscosity at 25 °C	ASTM D88	75	125
2	Flash point (tag open cup) °C	ASTM 3143	40	-
3	Density Kg/Ltr at 25 °C	ASTM D-41	0.85	0.90
4	Bitumen softening point °C	ASTM D36	90	100
5	Distillation:			
	Distillate, vol.% of total distillate to 360 °C:	ASTM D402		
	Up to 2250C		37	-
	Up to 3160		-	68
6	Tests on residue from distillation:	ASTM D5	25	50
	Penetration at 25°C, 0.1 mm			
7	solubility in trichloroethylene %	ASTM D2042	99	-
8	water, volume %	ASTM D-95	-	0.2
9	drying time at 25°C in hours		1	2

NOTE : THE ABOVE SHOWN TECHNICAL DATA ARE RESULTS OBTAINED IN LABORATORY AND EXTRA DETAILS CAN BE PROVIDED UPON REQUEST. IN ACCORDANCE TO ASTM AND UEAtc STANDARDS RESULTS ARE SUBJECTED TO A VARIATION OF 20 % .



izomaks
PRIMER D-41

izomax PRIMER D-41 is a premium quality , cold applied , fast curing primer, complies with the requirements and specifications of ASTM D-41 standard, Which is blended with selective grade of oxidized bitumen and fast curing solvents, wetting and saturation additives

USES

izomax PRIMER D-41 is a universal primer that can be use concrete roofing, brick, metal wall surface and waterproofing below or above ground level. It helps to the waterproofing materials adhere batter to the application of modified bitumen membranes

STROAGE

izomax PRIMER D-41 should be stored under ventilated covered store at temperature between 5°C and 30°C. The shelf life of 24 months can be expected for unopened containers stored properly.

APPLICATION

The surface to be waterproofed should be clean, dry and free from oil, grease and any other foreign matters. IZOMAKS PRIMER D-41 should be thoroughly stirred before use and applied to the substrate by soft brush, roller or spray at the rate of (200-300)g/m2 . Before application of subsequent layers should allowed to dry

PACKAGING

Available in 200kg, 100kg and 18Ltr.

COVERAGE

at the rate of (0.2-0.3) kg/m2 by roller, soft brush or spray to dump or dry surfaces.

CLEANING

TOOLS Clean with petroleum solvents.

HANDS Use a hand cleaner or solvent followed by soap and water.

STANDARD

Exceed the performance requirements of ASTM D-41.

HEALTH & SAFTY

Contains petroleum grades of solvent; flammable; keep away from open fire, spark or other ignition sources. were protective cloths, safety shoe, gloves, and goggles.

HEALTH & SAFTY

FIRE Flammable when wet flash point 40c.

SKIN Avoid repeated or prolonged skin contact; if contact occurs remove with hand cleaner that removes oil and grease; when clean with soap and water.

EYES No special precautions required. But if eyes contact cause irritation. flush with clean water.

izomaks
PRIMER D-41

